

schedule 120 for Plain-End Pipe
(Data from ASME B36.10 (incorporating ASTM A53 Table 2.2))

DN	NPS	Outside Diameter		Wall Thickness		Plain End Mass		Identification	Schedule No.
		mm	in	mm	in	kg/m	lb/ft		
100	4	114.3	4.500	11.13	0.438	28.32	19.02		120
125	5	141.3	5.563	12.7	0.500	40.28	27.06		120
150	6	168.3	6.625	14.27	0.562	54.21	36.43		120
200	8	219.1	8.625	18.26	0.719	90.44	60.77		120
250	10	273.0	10.750	21.44	0.844	133.01	89.38		120
300	12	323.8	12.750	25.4	1.000	186.92	125.61	XXS	120
350	14	355.6	14.000	27.79	1.094	224.66	150.93		120
400	16	406.4	16.000	30.96	1.219	286.66	192.61		120
450	18	457	18.000	34.93	1.375	363.58	244.37		120
500	20	508	20.000	38.1	1.500	441.52	296.65		120
550	22	559	22.000	41.28	1.625	527.05	353.94		120
600	24	610	24.000	46.02	1.812	640.07	429.79		120